

ISO 9001:2015	Document No: TM/HM/6/540	Version No:0.0	Date effective: 11/10/2023
Specification of Connecting Piece for vibration drive of Unimat-4S (Part no. CU20.103)			



RESEARCH DESIGN AND STANDARD ORGANISATION
Manak Nagar, Lucknow-226011

Track Machine and Monitoring Directorate

SPECIFICATION NO.TM/HM/6/540
SPECIFICATION OF CONNECTING PIECE FOR VIBRATION DRIVE OF UNIMAT-4S
(PART NO. CU20.103)

DTM-VI	EDTM	Page 1 of 3
Prepared By:	Issued By:	

ISO 9001:2015	Document No: TM/HM/6/540	Version No:0.0	Date effective: 11/10/2023
Specification of Connecting Piece for vibration drive of Unimat-4S (Part no. CU20.103)			

SPECIFICATION NO.TM/HM/6/540

SPECIFICATION OF CONNECTING PIECE FOR VIBRATION DRIVE OF UNIMAT-4S (PART NO. CU20.103)

- 1.0 Scope:** This specification covers the dimensional, functional and material requirements with testing criteria of connecting piece for vibration drive of Unimat-4S. This specification may be treated as provisional subject to modifications based on service performance.
- 2.0 Reference documents:** Following documents have been referred to in this specification. Full sets of relevant drawings and the referred codes/ specifications, duly incorporating the up-dated corrections/amendments, shall be available for reference at manufacturer's works.
- i) BS:970 - 1991 – Case hardening Alloy Steel - specification.
 - ii) IS:77-1976 - Linseed oil for paints - specification.
 - iii) RDSO Drg. No.- RDSO/TM/10/23 Connecting piece for vibration drive of Unimat-4S.
- 3.0 Functional requirement:** It is provided between vibration shaft and hydraulic motor to transfer the rotational power from motor to shaft. All surfaces meant for machining shall be finished as mentioned in the drawing no. RDSO/TM/10/23.
- 4.0 Dimension & Tolerance:** Dimensions and tolerances of Connecting Piece shall be as mentioned in RDSO drawing no. RDSO/TM/10/23.
- 5.0 Material:** The Connecting Piece shall be made from case hardening alloy steel grade 815M17 (En-353) conforming to BS:970-1991–Case hardening Alloy Steel.
- 6.0 Manufacturing Process:** Connecting Piece shall be made by forging and machining process of specified material.
- 7.0 Heat treatment:** Connecting Piece shall be heat treated with any suitable methods to achieve case hardness 43 to 47 HRC.
- 8.0 Marking:** Month and year of manufacture and manufacturer's code / identification shall be engraved / embossed on the non-functioning surface of Connecting Piece.
- 9.0 Inspection and Acceptance Criteria:**
- i) Each component offered by manufacturer shall be checked visually for their surface finish, freedom from defect like porosity, cracks, improper edges etc. Machined surface shall be checked by any suitable pneumatic or electronic equipment.

DTM-VI	EDTM	Page 2 of 3
Prepared By:	Issued By:	

ISO 9001:2015	Document No: TM/HM/6/540	Version No:0.0	Date effective: 11/10/2023
Specification of Connecting Piece for vibration drive of Unimat-4S (Part no. CU20.103)			

- ii) The component found suitable after visual inspection shall be checked for their dimensional characteristics as per relevant drawing.
- iii) Supplier shall produce the certificate that the raw material used for manufacturing of the component conforms to material specified as mentioned in Para 5.0.
- iv) Minimum one or 2% of sample randomly picked up from each lot of consignment shall be checked for their hardness as per para no.7.0.
- v) Minimum one no or 2 % sample of component randomly picked up out of each lot of consignment and shall be subjected to chemical composition test. The consignee shall test the material for chemical composition at his laboratory or get the material tested in a reputed (NABL accredited or accredited by other international body like APLAC, MRA, ILAC etc) laboratory having proper facilities for testing. Before sending the samples for testing, the same shall be duly sealed and secret coding shall be done.
- vi) Any deviations in the test result from the requirement of the specification and drawing shall be the cause of rejection.

10.0 Packing and Protection: Each component shall be protected with one coat of boil linseed oil conforming to IS: -77-1976 (linseed oil for paint) and shall be packed in card board case.

DTM-VI	EDTM	Page 3 of 3
Prepared By:	Issued By:	