

## RESEARCH DESIGNS AND STANDARDS ORGANISATION Manak Nagar, Lucknow-226011

**Track Machines and Monitoring** 

FUNCTIONAL REQUIREMENT SPECIFICATION NO. TM/HM/6/FRS/003
FUNCTIONAL REQUIREMENT SPECIFICATION OF TAMPING ARM BOLT WITH DISC, HEX NUT & SPRING WASHER FOR UNIMAT (MPT/MFI)

(Date Effective: 19/12/2024)

## FUNCTIONAL REQUIREMENT SPECIFICATION NO. TM/HM/6/FRS/003

## FUNCTIONAL REQUIREMENT SPECIFICATION OF TAMPING ARM BOLT WITH DISC, HEX NUT & SPRING WASHER FOR UNIMAT (MPT/MFI)

- **1.0 Scope**: This functional requirement specification covers the dimensional, functional and material requirements with testing criteria of Tamping Arm Bolt with Disc, Hex Nut & Spring Washer for Unimat. This functional requirement specification may be treated as provisional subject to modifications based on service performance.
- **2.0 Reference Documents:** Following documents have been referred to in this functional requirement specification. Full sets of relevant drawings and the referred codes/specifications, duly incorporating the up-dated corrections/amendments, shall be available for reference at manufacturer's works.
  - i) BS: 970 Part II Direct hardening alloy steel Specification.
  - ii) IS: 2062 -1992 -Steel for general engineering purpose–Specification.
  - iii) IS: 77-1976 Linseed oil for paints Specification.
  - iv) RDSO Drg. No. RDSO/TM/23/24 Tamping Arm Bolt with Disc, Hex Nut & Spring Washer for Unimat.
- **3.0 Functional Requirement:** Tamping Arm Bolt with Disc, Hex Nut & Spring Washer is provided in the tamping bank to hold the tamping arm. Tamping arms move about it. It shall be capable to resist impact load of tamping bank and squeezing pressure coming on tamping arm through it. All surfaces meant for machining shall be finished as mentioned in the drawing.
- **4.0 Dimension & Tolerance:** Dimensions and tolerances of Tamping Arm Bolt with Disc, Hex Nut & Spring Washer shall be as mentioned in RDSO drawing no. RDSO/TM/23/24.
- **Material:** The Tamping Arm Bolt shall be made from Steel of Grade 709 M 40 (EN-19) conforming to BS: 970 Part-II Specification of direct hardening alloy steel. Disc, Hex Nut & Spring Washer shall be made from steel grade A or B (mild Steel) conforming to IS: 2062-1992.
- **6.0 Manufacturing Process**: Tamping Arm Bolt shall be made by closed die forging only under belt drop forged hammer of adequate capacity capable of delivering minimum energy or force required for deformation during closed dieforging. Forging shall be machined to get final shape.
- **7.0 Heat Treatment:** Heat treatment of each component shall be done by induction hardening process to achieve case hardening of 57-60 HRC upto 1.00 mm depth.

**8.0 Marking:** Month and year of manufacture and manufacturer's code / identification shall be engraved / embossed on the non-functional surface of Tamping Arm Bolt, Disc & Hex Nut.

## 9.0 Inspection And Acceptance Criteria:

- Each components offered by manufacturer shall be checked visually for their surface finish, freedom from defects like porosity, cracks, improper edges etc. Machined surface shall be checked by any suitable pneumatic or electronic equipment.
- ii) The component found suitable after visual inspection, shall be checked for their dimensions as per relevant drawing.
- iii) Minimum one or 2% of sample randomly picked up from each lot of consignment shall be checked for their hardness as per para no.7.0.
- iv) Supplier shall produce the certificate that the raw material used for manufacturing of Tamping Arm Bolt conforms to the Grade 709 M 40 (EN-19) of BS: 970 Part-II & others shall be conforming to steel grade A or B (mild steel) of IS: 2062-1992.
- v) Minimum one no or 2 % sample of the component of each lot of consignment and shall be subjected to chemical composition test. The consignee shall test the material for chemical composition at his laboratory or get the material tested in a reputed (NABL accredited or accredited by other international body like APLAC, MRA, ILAC etc) laboratory having proper facilities for testing. Before sending the samples for testing, the same shall be duly sealed and secret coding shall be done.
- vi) Any deviations in the test result from the requirement of the specification and drawing shall be the cause of rejection.
- **10.0 Packing and Protection**: Each component shall be protected with one coat of boiled linseed oil conforming to IS: 77-1976 (linseed oil for paint) and shall be packed in cardboard case or any other packing arrangement as per best trade practice.

\*\*\*